


3-D Polymer Coating (P)



The NEXTERION® 3-D Polymer coating is the ideal surface for the covalent immobilization of biomolecules containing primary amines (NH₂ groups) such as proteins, antibodies and most peptides. Furthermore, for amino-modified biomolecules like glycans or oligonucleotides this surface may be the coating of choice. SCHOTT specifically developed the 3-D Polymer coating as a dedicated substrate surface for printing low-density antibody microarrays. It produces excellent signal-to-background ratios, and exceptionally wide dynamic ranges compared to conventional “two-dimensional” coatings through a unique combination of low non-specific binding characteristics, and high probe loading capacity. Produced in ISO class 5 clean room conditions using a proprietary thin-film deposition process and running a stringent quality control system, the 3-D Polymer coating is offered in standard and custom formats.

Product Information

Coating Chemistry



NEXTERION® 3-D Polymer coating chemistry

Shelf Life

Twelve months for sealed packages when stored at -20°C.


Immobilization Method

Covalent binding via amine reactive chemistry.

Probe Types

- Amino-linked glucans
- Antibodies and antibody fragments
- Functional proteins such as enzymes or receptors
- Small protein fragments such as peptides
- Amino-modified oligonucleotides 16 to 70 mers





Advantages

Material

- High-quality borosilicate glass
- Alternative substrate materials can be offered

Formats

- Standard sizes (slide format, SBS plate format)
- Customized dimensions and thicknesses

Structuring

- Pre-scoring
- Hydrophobic coating for multiplexing

Markings

- Barcodes (1D e.g. code 39, code 128; 2D e.g. QR, data matrix)
- Logos
- Position markings and fiducials

Quality

- Proprietary thin-film deposition process optimized by SCHOTT
- Excellent intra- and inter-lot reproducibility
- Physical and functional quality control
- ISO class 5 clean room production
- Relevant processes in place for diagnostic company needs

Supply Forms

Product	Size (mm)	Thickness (mm)	Pieces per pack
Slide P, barcoded	75.6 x 25.0	1.0	25
Plate P	110.0 x 74.0	1.0	5
Customized P	Variable	0.170–2.5	Variable



SCHOTT Technical Glass
Solutions GmbH
Otto-Schott-Straße 13
D-07745 Jena, Germany
Phone +49 (0)3641/681-4066
Fax +49 (0)3641/681-4970
info.nexterion@schott.com

www.schott.com/nexterion

SCHOTT
glass made of ideas